

Mélange à béton 0/22.4 (paveur)

Pétrographie : Alluvions silico-calcaires

FTP Mélange 0/22.4 04.2023

Partie normative

Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire

0 22.4

Code

Producteur


	0.063	0.25	0.5	1	2	4	11.2	22.4	31.5	45	AS	f	FM	LA	MB	S	W	WA24	
Etendue e	6			40		40		10				6	0.6						
V.S.S.	6.00			60.00		90.00		99.00			0.20	6.0		20	1.5	0.40			2.5
V.S.I.				20.00		50.00		85.00	98.00	100.00									

Partie informative

Résultats de production

du 25/01/23 au 16/03/23

	0.063	0.25	0.5	1	2	4	11.2	22.4	31.5	45	AS	f	FM	LA	MB	S	W	WA24	
Maximum	4.28	14.15	23.51	31.75	42.61	56.41	75.57	95.69	100.00	100.00		4.3	4.45		1.0			3.8	
Xf+1.25/Ecart-types	4.40	13.53	23.37	32.37	42.46	56.16	75.44	95.64	100.00	100.00		4.4	4.45		1.1			3.7	
Moyenne Xf	3.91	11.35	22.36	29.93	40.56	53.33	74.11	94.97	100.00	100.00	0.03	3.9	4.35	19	1.0	<0.01%		3.1	0.7
Xf-1.25/Ecart-types	3.41	9.17	21.35	27.50	38.65	50.50	72.77	94.30	100.00	100.00		3.4	4.25		0.8			2.5	
Minimum	3.27	9.59	21.26	26.65	38.52	50.87	72.93	94.26	100.00	100.00		3.3	4.27		0.8			2.5	
Ecart-type	0.397	1.742	0.808	1.948	1.526	2.266	1.068	0.537	0.000	0.000		0.40	0.080		0.10			0.50	
Nombre de résultats	4	4	4	4	4	4	4	4	4	4	1	4	4	1	4	1	4	1	



Delphine VILLEGER

Villeger