

# 0/4 M

**Péetrographie :** Alluvions silico-calcaires  
**Elaboration :** Semi-Concassé

FTP 0/4M 1er semestre 2024

## Partie normative

Valeurs spécifiées sur lesquelles le producteur s'engage

### Classe granulaire

0	4
---	---

### Norme

Norme NF P 18-545 Article 10 - EN 12620

### Code

A


	0.063	0.125	0.25	0.5	1	2	D	1.4D	2D	Ab	AS	f	FM	MB	S
Etendue e	6		40		40		10	5				6			
V.S.S.+U	10.0		42		82		100					10.0	3.50	2.0	
V.S.S.	9.0		40		78		98			2.5	0.20	9.0	3.35	1.5	0.40
V.S.I.	3.0		0		38		88	95	100			3.0	2.75		
V.S.I.-U	2.0		0		34		86	94				2.0	2.60		

## Partie informative

Résultats de production

du 06/07/23 au 12/12/23

	0.063	0.125	0.25	0.5	1	2	4	5.6	8	Ab	AS	f	FM	MB	S
Maximum	8.5	16	23	49	60	73	96	100	100			8.5	3.34	0.8	
Xf+1.25xEcart-types	6.2	11	20	46	58	72	94	100	100			6.2	3.31	0.8	
Moyenne Xf	4.7	8	18	41	53	69	92	100	100	0.9	0.06	4.7	3.19	0.7	<0.01%
Xf-1.25xEcart-types	3.2	6	16	36	48	66	90	100	100			3.2	3.07	0.5	
Minimum	3.0	6	16	33	46	64	90	99	100			3.0	3.00	0.5	
Ecart-type	1.20	2.2	1.8	4.0	4.1	2.5	1.5	0.2	0.0			1.20	0.100	0.20	
Nombre de résultats	18	18	18	18	18	18	18	18	18	1	1	18	18	18	1



Delphine VILLEGER

*Villeger*